

Application No.: 10/735,252

Docket No.: JCLA10634

AMENDMENTS**In the Claims:**

Please amend the claims according to the following listing of claims and substitute it for all prior versions and listings of claims in the application.

1. (currently amended) An emulsion type adhesive applicable for over-laminating films, the emulsion type adhesive comprising:

(a) 60 to 99.5 parts per hundred of monomers of one or more alkyl acrylates containing 4-12 carbon atoms ~~on an~~ in the alkyl group;

(b) 0.5 to 40 parts per hundred of monomers of an alkyl acrylate or alkyl methacrylate containing 1-3 carbon atoms in an the alkyl group;

(c) 0.1 to 5 parts per hundred of monomers of dicarboxylic acids;

(d) 1 to 5 parts per hundred of a reactive surfactant;

(e) 0.1 to 15 parts per hundred of an organic acid vinyl ester; and

(f) 100 parts per hundred of soft water,

wherein a total weight of (a) and (b) is 100 parts by hundred, while (c), (d), (e) and (f) are calculated relative to the total weight of (a) and (b).

Claim 2. (canceled).

Application No.: 10/735,252

Docket No.: JCLA10634

3. (currently amended) The emulsion type adhesive of claim 1-~~or~~2, wherein the alkyl acrylate containing 4-12 carbon atoms ~~on~~in the alkyl group is selected from the group consisting of butyl acrylate, 2-ethyl hexyl acrylate, i-butyl acrylate, n-triethyl acrylate and i-octyl acrylate.

4. (original) The emulsion type adhesive of claim 1, wherein the alkyl acrylate containing 1-3 carbon atoms in the alkyl group is ethyl acrylate or methyl acrylate

5. (currently amended) The emulsion type adhesive of claim 2-1, wherein the alkyl methacrylate containing 1-6~~3~~ carbon atoms in the alkyl group is ~~selected from the group consisting of methyl methacrylate or ethyl methacrylate and butyl methacrylate.~~

6. (currently amended) The emulsion type adhesive of claim 1-~~or~~2, wherein the dicarboxylic acid is selected from the group consisting of maleic acid, fumaric acid, itaconic acid and citraconic acid.

7. (currently amended) The emulsion type adhesive of claim 1-~~or~~2, wherein the reactive surfactant is selected from the group consisting of an allyl surfactant, an 2-propenyl surfactant, a maleic surfactant, an itaconic surfactant and an acryl surfactant.

8. (currently amended) The emulsion type adhesive of claim 1-~~or~~2, wherein the organic acid vinyl ester is selected from the group consisting of vinyl acetate, vinyl butyrate, vinyl propionate, vinyl isobutyrate and vinyl 2-ethyl hexoate.

9. (currently amended) A method for preparing an emulsion type adhesive applicable for over-laminating films, the method comprising:

(a) mixing an alkyl acrylate containing 4-12 carbon atoms ~~on~~an ~~an~~in the alkyl group, an alkyl acrylate containing 1-3 carbon atoms in ~~an~~the alkyl group or an alkyl methacrylate

Application No.: 10/735,252

Docket No.: JCLA10634

containing 1-~~6~~3 carbon atoms in ~~an~~ the alkyl group, a dicarboxylic acid, soft water and an organic acid vinyl ester, and then adding a reactive surfactant so as to obtain a pre-emulsion; and

(b) adding at least an oxidizing agent and a reducing agent to the pre-emulsion, followed by stirring, heating and reacting to obtain an emulsion type adhesive.

10. (original) The method of claim 9, wherein a heating temperature in the step (b) is about 25°C-55°C.

11. (currently amended) The method of claim 9, wherein the alkyl acrylate containing 4-12 carbon atoms ~~on~~in the alkyl group is selected from the group consisting of butyl acrylate, 2-ethyl hexyl acrylate, i-butyl acrylate, n-triethyl acrylate and i-octyl acrylate.

12. (original) The method of claim 9, wherein the alkyl acrylate containing 1-3 carbon atoms in the alkyl group is ethyl acrylate or methyl acrylate

13. (currently amended) The method of claim 9, wherein the alkyl methacrylate containing 1-~~6~~3 carbon atoms in the alkyl group is ~~selected from the group consisting of methyl methacrylate or ethyl methacrylate and butyl methacrylate.~~

14. (original) The method of claim 9, wherein the dicarboxylic acid is selected from the group consisting of maleic acid, fumaric acid, itaconic acid and citraconic acid.

15. (original) The method of claim 9, wherein the reactive surfactant is selected from the group consisting of an allyl surfactant, an 2-propenyl surfactant, a maleic surfactant, an itaconic surfactant and an acryl surfactant.

Application No.: 10/735,252

Docket No.: JCLA10634

16. (original) The method of claim 9, wherein the organic acid vinyl ester is selected from the group consisting of vinyl acetate, vinyl butyrate, vinyl propionate, vinyl isobutyrate and vinyl 2-ethyl hexoate.

17. (original) The method of claim 9, wherein the oxidizing agent is t-butyl peroxide and the reducing agent is Rongalite.

18. (currently amended) An over-laminating tape comprises an emulsion type adhesive as claimed in claim 1 ~~or claim 2~~, wherein the over-laminating tape is fabricated by coating the type adhesive as claimed in claim 1 ~~or claim 2~~ onto a surface of a transparent plastic film.